METAPAPER

the future of real communication

EXTRAMATT Coldwhite Datasheet

Grammage	ISO 536	gsm	115	130	145	165	300	400
							laminated	laminated
Thickness	ISO 534	µm	126,5	143	166,75	191,4	372	512
Bulk	ISO 534	cm3/g	1,10	1,10	1,15	1,16	1,24	1,28
Roughness Bendtsen	ISO 8791-2	ml/min	160	160	160	160	200	200
Smoothness Bekk	ISO 5627	s	30	30	30	30	20	20
Brightness	ISO 2471 (D65)	%	105	105	105	105	105	105
Opacity	ISO 2471	%	93	95	96	97	99	99
Whiteness	ISO 11475	%	160	160	160	160	160	160
Indigo			developed for Indigo					
Scodix			developed for Skodix					
Additional print processes			Toner, Letterpress (from 300gsm onwards), Offset					
Suitable for preprint			yes	yes	yes	yes		

Tolerances ±

Grammage	ISO 536	gsm	5	6	10	11	12	12
Thickness	ISO 534	µm	6	8	10	16	17	17
Bulk	ISO 534	cm3/g						
Roughness Bendtsen	ISO 8791-2	ml/min	40	40	40	40	45	45
Smoothness Bekk	ISO 5627	s	9	9	9	9	10	10
Brightness	ISO 2471 (D65)	%	2	2	2	2	2	2
Opacity	ISO 2471	%	2	2	2	2	2	2
Whiteness	ISO 11475	%	3	3	3	3	3	3

Certificatee FSC Mix: SGSCH-COC-009212

METAPAPER

the future of real communication

EXTRAMATT White Datasheet

Grammage	ISO 536	gsm	115	130	145	165	300	400
							laminated	laminated
Thickness	ISO 534	µm	126,5	143	169,65	198	372	512
Bulk	ISO 534	cm3/g	1,10	1,10	1,17	1,20	1,24	1,28
Roughness Bendtsen	ISO 8791-2	ml/min	120	120	120	120	120	120
Smoothness Bekk	ISO 5627	s	30	30	30	30	30	30
Brightness	ISO 2471 (D65)	%	105	105	105	105	105	105
Opacity	ISO 2471	%	94	95	96	97	99	99
Whiteness	ISO 11475	%	138	138	138	138	138	138
Indigo			developed for Indigo					
Scodix			developed for Skodix					
Additional print processes			Toner, Letterpress (from 300gsm onwards), Offset					
Suitable for preprint			yes	yes	yes	yes		

Tolerances ±

Grammage	ISO 536	gsm	5	6	10	11	10	11
Thickness	ISO 534	µm	6	8	10	16	16	16
Bulk	ISO 534	cm3/g						
Roughness Bendtsen	ISO 8791-2	ml/min	40	40	40	40	40	40
Smoothness Bekk	ISO 5627	s	9	9	9	9	9	9
Brightness	ISO 2471 (D65)	%	2	2	2	2	2	2
Opacity	ISO 2471	%	2	2	2	2	2	2
Whiteness	ISO 11475	%	3	3	3	3	3	3

Certificatee FSC Mix: SGSCH-COC-009212