

NEWSPRINT Datasheet

Grammage	ISO 536	gsm	80
Thickness	ISO 534	µm	90 - 100
Bulk	ISO 534	cm ³ /g	1,1-1,3
Roughness Bendtsen	ISO 8791-2	ml/min	205
Smoothness Sheffield	ISO 8791-3	s	
Brightness	ISO 2471 (D65)	%	
Opacity	ISO 2471	%	96
Whiteness	ISO 11475	%	81
Indigo			suitable since lightly pigmented
Additional print processes			Toner, Riso, Offset
Suitable for preprint			yes

Tolerances ±

Grammage	ISO 536	gsm	2
Thickness	ISO 534	µm	
Bulk	ISO 534	cm ³ /g	
Roughness Bendtsen	ISO 8791-2	ml/min	
Smoothness Sheffield	ISO 8791-3	s	
Brightness	ISO 2471 (D65)	%	
Opacity	ISO 2471	%	
Whiteness	ISO 11475	%	

Certificate

FSC SGSCH-COC-00921 FSC Mix EU Ecolabel
lifespan class 6-40 (Durability of at least 50 years)

GREEN RESPONSIBILITY

ECF (elementary chlorine free)
from recycled waste paper fiber