

PURE COTTON / T-SHIRT Datasheet

T-Shirt

Grammage	ISO 536	gsm	350	710	350	710	324
Shade			White	White	Warmwhite	Warmwhite	White
				laminated		laminated	
Thickness	ISO 534	µm	560	1136	560	1136	457
Bulk	ISO 534	cm ³ /g	1,6	1,6	1,6	1,6	1,4
Roughness Bendtsen	ISO 8791-2	ml/min	1400	1400	1400	1400	350
Brightness	ISO 2471 (D65)	%	1,0	1,0	1,5	1,5	92
Opacity	ISO 2471	%					98
Whiteness	ISO 11476	%	142	142	77	77	140
Indigo			no > Toner	no	no > Toner	no	cert./i-Tone
Additional print processes			Toner (324gsm and 350gsm), Letterpress, Offset (only platen press)				

Tolerances ±

Grammage	ISO 536	gsm	18	36	18	36	
Thickness	ISO 534	µm	38	74	38	74	
Bulk	ISO 534	cm ³ /g					
Roughness Bendtsen	ISO 8791-2	ml/min	250	250	250	250	
Brightness	ISO 2471 (D65)	%					
Opacity	ISO 2471	%					
Whiteness	ISO 11475	%	3	3	3	3	

Certificate:

very good resistance against climatic conditions: humidity, heat, cold
Cotton, no wood fiber, hence not FSC certifiable

GREEN RESPONSIBILITY

alternative fiber: cotton
Pure Cotton: 100% cotton
T-Shirt: 100% recycled cotton (T-Shirts)