

**PURE COTTON Datasheet**

Grammage	ISO 536	g/m2	350	710	350	710
Shade			White	White	Warmwhite	Warmwhite
Grain direction (source format)	70 x 100		LG	LG *	LG	LG *
Thickness	ISO 534	µm	560	1136	560	1136
Bulk	ISO 534	cm3/g	1,6	1,6	1,6	1,6
Roughness Bendtsen	ISO 8791-2	ml/min	1400	1400	1400	1400
Brightness	ISO 2471 (D65)	%	1,0	1,0	1,5	1,5
Opacity	ISO 2471	%				
Whiteness	ISO 11476	%	142	142	77	77
Indigo			no > Toner	no	no > Toner	no
Additional print processes			Toner (324gsm and 350gsm), Letterpress, Offset (only platen press)			

**Tolerances ±**

Grammage	ISO 536	g/m2	18	36	18	36
Thickness	ISO 534	µm	38	74	38	74
Bulk	ISO 534	cm3/g				
Roughness Bendtsen	ISO 8791-2	ml/min	250	250	250	250
Brightness	ISO 2471 (D65)	%				
Opacity	ISO 2471	%				
Whiteness	ISO 11475	%	3	3	3	3

**GREEN RESPONSIBILITY**

100% cotton

\* laminated

very good resistance against climatic conditions: humidity, heat, cold