

MULTILOFT Datasheet

			extrarough						
Surface	COVER		RECYCLING*	extrarough	extrarough	extrarough	extrarough	extrasmooth	Magnet
Shade	46 x 32		white	white	warmwhite	earth	black	coldwhite	
Grammage	ISO 536	g/m2	325	240	240	270	270	270	1350
Thickness	ISO 534	µm	419	356	356	305	305	305	530
Indigo				certified					
Additional print processes				Toner, Letterpress, Offset					

Surface	TOP		extrarough	Photo
Shade	46 x 32		white	white
Grammage	ISO 536	g/m2	150	190
Thickness	ISO 534	µm	201	184
Indigo			certified	
Additional print processes			Toner,Offset	X

MultiLoft is a unique, special application substrate, and as such, not subject to the same 1 cm or less sheet curl specification as non-treated sheets. Application of glues and/or coatings may lead to curling in excess of 1 cm, requiring the operator to apply back-curling massage of the stack prior to running through the press or printer.

INSERTS	C / M / Y / K	g/m2	µm
Coldwhite	2 / 0 / 0 / 0	325	406
White	0 / 0 / 0 / 0	325	406
Warmwhite	0 / 0 / 5 / 0	325	406
Black	0 / 0 / 0 / 100	270	356
Earth	0 / 80 / 60 / 0	270	356
Red	0 / 100 / 80 / 10	270	356
Dark Green	50 / 10 / 100 / 5	270	356
Light Green	30 / 0 / 40 / 0	270	356
Turquoise	50 / 0 / 20 / 0	270	356
Purple	40 / 60 / 0 / 0	270	356
Yellow	0 / 10 / 90 / 0	270	356
Orange	0 / 40 / 90 / 0	270	356
Magenta	0 / 100 / 0 / 0	270	356
Pink	0 / 40 / 5 / 0	270	356
Blue	100 / 30 / 0 / 10	270	356

Shelf life: dependent on environmental conditions (temperature, humidity, etc.): 1.5 - 2.5 years
 Sealing pressure: > 22 kg/cm2

GREEN RESPONSIBILITY

Cover coldwhite, white, warmwhite and Insert white:
 FSC Mix: SGSCH-COC-009212

Cover/Insert earth und Cover/Insert Black is source material certified (before coating)

Adhesive completely chemical-free:
 rubber-based and water-based