

PROPHOTO LUSTRE White Datasheet

Grammage	ISO 536	g/m ²	190
Grain direction (source format)	50 x 70		LG
Thickness	ISO 534	µm	190
Bulk	ISO 534	cm ³ /g	1,0
Roughness Bendtsen	ISO 8791-2	ml/min	
Smoothness Sheffield	ISO 8791-3	s	
Brightness	ISO 2471 (D65)	%	92
Opacity	ISO 22469	%	> 92
Whiteness	ISO 2469	%	> 140
Glanz	ISO 2813		30
Indigo			certified
Additional print processes			Toner (Ricoh)

Tolerances ±

Grammage	ISO 536	g/m ²	6
Thickness	ISO 534	µm	6
Bulk	ISO 534	cm ³ /g	
Roughness Bendtsen	ISO 8791-2	ml/min	
Smoothness Sheffield	ISO 8791-3	s	
Brightness	ISO 2471 (D65)	%	
Opacity	ISO 22469	%	
Whiteness	ISO 2469	%	
Glanz	ISO 2813		5

GREEN RESPONSIBILITY

FSC Mix: SGSCH-COC-009212

high ageing resistance (200+ years)

no stress whitening / fold break (even without lamination or grooving)

resistant to water, oil and dirt, removable with disinfectant