

EMBOSSSED Datasheet
Leather, Linen, Micro, Stone - one-sided embossing

Grammage	ISO 536	g/m2	300	Coldwhite	White	Warmwhite
Grain direction (source format)	100 x 72		SG			
Thickness	ISO 534	µm	375			
Bulk	ISO 534	cm3/g	1,2			
Roughness Bendtsen	ISO 8791-2	ml/min				
Smoothness Sheffield	ISO 8791-3	s				
Brightness	ISO 2471 (D65)	%				
Opacity	ISO 2471	%	97			
Whiteness	ISO 11475	%		162	148	120
Indigo			*			
Additional print processes			Toner, Letterpress, Offset			

Tolerances ±

Grammage	ISO 536	g/m2	7			
Thickness	ISO 534	µm	8			
Bulk	ISO 534	cm3/g				
Roughness Bendtsen	ISO 8791-2	ml/min				
Smoothness Sheffield	ISO 8791-3	s				
Brightness	ISO 2471	%				
Opacity	ISO 2471	%				
Whiteness	ISO 11475	%		3	3	3

GREEN RESPONSIBILITY

FSC Mix: SGSCH-COC-009212

* Raw material (before embossing) certified.
 adjustments required - depending on machine type,
 (lower temperature - in case of a 7s series:
 adjustments in transfer profile / contact pressure)
 Caution in solids (in particular with Micro).